



**SHERWIN
WILLIAMS.**

Pro Industrial™ Pro-Cryl®

Universal Primer

B66-1300 Series

CHARACTERISTICS

Pro Industrial Pro-Cryl® Universal Primer is an advanced technology, self-cross-linking acrylic primer. It is rust inhibitive and was designed for both construction and maintenance applications. It can be used as a primer under water-based or solvent-based high-performance topcoats.

Features:

- Rust inhibitive, corrosion resistant
- Single component
- Early moisture resistant
- Fast dry
- Lower temperature application 35°F
- Interior and exterior use
- Suitable for use in USDA inspected facilities

For use on properly prepared:

Steel, Galvanized & Aluminum, Wood

Finish: Low Sheen

Color: Off White, Medium Grey, and Red Oxide

Recommended Spreading Rate per coat:

Wet mils: 5.0-10.0
 Dry mils: 1.9-3.8
 Coverage: 160-320 sq. ft. per gallon
 Theoretical Coverage: 609 sq. ft. per gallon
 @ 1 mil dry

Approximate spreading rates are calculated on volume solids and do not include any application loss.

Note: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

Drying Schedule @ 6.0 mils wet, @ 50% RH:

Drying and recoat times are temperature, humidity, and film thickness dependent.

	@40°F	@77°F	@120°F
To touch	2 hours	40 minutes	20 minutes
Tack free	8 hours	2 hours	1 hour
To recoat	16 hours	4 hours	2 hours

Tinting: DO NOT TINT

Extra White B66W01310

(may vary by color)

V.O.C. (less exempt solvents):

less than 50 grams per litre; 0.42 lbs. per gallon
 As per 40 CFR 59.406

Volume Solids: 38 ±2%
Weight Solids: 50 ±2%
Weight per Gallon: 10.09 lbs
Flash Point: N/A
Shelf Life: 36 months, unopened

COMPLIANCE

As of 2/05/2026, Complies with:

OTC	Yes
OTC Phase II	Yes
S.C.A.Q.M.D.	Yes
CARB	Yes
CARB SCM 2007	Yes
CARB SCM 2020	Yes
Canada	Yes
LEED® v4 & v4.1 Emissions	Yes
LEED® v4 & v4.1 V.O.C.	Yes
EPD-NSF® Certified	Yes
MIR-Manufacturer Inventory	Yes
MPI®	#107, 107 X-Green™, 134

APPLICATION

Temperature:
 minimum 35°F / 1.6°C
 maximum 120°F / 48.8°C
 air, surface and material
 At least 5°F above dew point

Relative humidity: 85% maximum
 The following is a guide. Changes in pressures and tip sizes may be needed for proper spray characteristics. Always purge spray equipment before use with listed reducer. Any reduction must be compatible with the existing environmental and application conditions.

Reducer: Water
Airless Spray:
 Pressure 2000 p.s.i.
 Hose 1/4 inch I.D.
 Tip .015-.019 inch
 Filter 60 mesh

Conventional Spray:
 Gun Binks 95
 Fluid Nozzle 66
 Air Nozzle 63 PB
 Atomization Pressure 60 p.s.i.
 Fluid Pressure 25 p.s.i.

Reduction: As needed up to 5% by volume
Brush: Nylon-polyester, such as Purdy® XL®
Roller Cover: 3/8 inch woven, such as Contractor Series® Soft Woven
 If specific application equipment is listed above, equivalent equipment may be substituted.

Apply paint at the recommended film thickness and spreading rate as indicated. Application of coating above maximum or below minimum recommended spreading rate may adversely affect coating performance.

Stripe coat crevices, welds, and sharp angles to prevent early failure in these areas. For best results on rusty surfaces, always apply first coat by brush.

When using spray application, use a 50% overlap with each pass of the gun to avoid holidays, bare areas, and pinholes. If necessary, cross spray at a right angle.

No painting should be done immediately after a rain or during foggy weather.

For optimal performance, this primer should be topcoated.

For exterior exposure, this primer should be topcoated within 14 days. If 14 days is exceeded remove all surface contamination by washing with an appropriate cleaner, rinse thoroughly and allow to dry. Finish with appropriate topcoat.

SPECIFICATIONS

Acceptable Water Based topcoats:

1-2 coats Pro Industrial Acrylic Coating or Pro Industrial Acrylic Dryfall
 Pro Industrial DTM Acrylic
 Pro Industrial Multi-Surface Acrylic
 Pro Industrial Pre-Catalyzed Epoxy
 Pro Industrial Pre-Catalyzed Urethane
 Pro Industrial Water Based Acrolon 100
 Pro Industrial Water Based Alkyd Urethane
 Pro Industrial Water Based Catalyzed Epoxy
 Sherwin-Williams Architectural Coatings

Acceptable Solvent Based topcoats:

Pro Industrial High Performance Epoxy
 Pro Industrial Industrial Enamels
 Tile Clad HS Epoxy

The finishes listed above are representative of the product's use. Other finishes may be appropriate.

Pro Industrial™ Pro-Cryl® Universal Primer

SURFACE PREPARATION

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Do not use hydrocarbon solvents for cleaning.

Remove all surface contamination by washing with an appropriate cleaner, rinse thoroughly and allow to dry. Existing peeled or checked paint should be scraped and sanded to a sound surface. Glossy surfaces should be sanded dull. Stains from water, smoke, ink, pencil, grease, etc. should be sealed with the appropriate primer-sealer. Recognize that any surface preparation short of total removal of the old coating may compromise the service length of the system.

Iron & Steel - Minimum surface preparation is Hand Tool Cleaning per SSPC-SP2. Remove all oil and grease from the surface per SSPC-SP1. For better performance, use Commercial Blast Cleaning per SSPC-SP6. Prime the area the same day as cleaned. Self priming.

Aluminum - Remove all oil, grease, dirt, oxide and other foreign material per SSPC-SP1. Self priming.

Galvanizing - Allow to weather a minimum of six months prior to coating. Solvent Clean per SSPC-SP1. When weathering is not possible, or the surface has been treated with chromates or silicates, first Solvent Clean per SSPC-SP1 and apply a test patch. Allow paint to dry at least one week before testing adhesion. If adhesion is poor, brush blasting per SSPC-SP16 is necessary to remove these treatments. Rusty galvanizing requires a minimum of Hand Tool Cleaning per SSPC-SP2, prime the area the same day as cleaned. Self priming.

Previously Painted Surfaces - If in sound condition, clean the surface of all foreign material. Smooth, hard or glossy coatings and surfaces should be dulled by abrading the surface. Apply a test area, allowing paint to dry one week before testing adhesion. If adhesion is poor, additional abrasion of the surface and/or removal of the previous coating may be necessary. Retest surface for adhesion. If paint is peeling or badly weathered, clean surface to sound substrate and treat as a new surface as above. Recognize that any surface preparation short of total removal of the old coating may compromise the service length of the system.

Wood - Surface must be clean, dry and sound. Prime with recommended primer. No painting should be done immediately after a rain or during foggy weather. Knots and pitch streaks must be scraped, sanded and spot primed before full coat of primer is applied. All nail holes or small openings must be properly caulked.

SURFACE PREPARATION

Mildew-

Clean mildew from the Surface: Mildew is a fungus that looks like dirt but won't wash off. Mildew must be removed before painting, or it will grow through any new coat of paint. To remove mildew or suspected mildew, scrub surface before painting with a commercial mildew remover following manufacturer's safety instructions.

PERFORMANCE

System Tested: (unless otherwise indicated)

Substrate: Steel

Surface Preparation: SSPC-SP10

Finish: 1 coat Pro Industrial Pro-Cryl Off White
1 coat Pro Industrial Acrylic Coating

Adhesion:

Method: ASTM D4541

Result: 500 p.s.i.

Corrosion Weathering:

Method: ASTM D5894, 10 cycles, 3360 hours

Result: Passes

Direct Impact Resistance:

Method: ASTM D2794

Result: greater than 140 inch lb.

Dry Heat Resistance:

Method: ASTM D2485

Result: 200°F

Flexibility:

Method: ASTM D522, 180° bend,

½ inch mandrel

Result: Passes

Moisture Condensation Resistance:

Method: ASTM D4585, 100°F, 1250 hours

Result: Passes

Pencil Hardness:

Method: ASTM D3363

Result: B

Salt Fog Resistance:

Method: ASTM B117, 1250 hours

Result: Passes

Provides performance comparable to products formulated In Lieu of federal specification: AA50557 and Paint Specification: SSPC-Paint 23.

SAFETY PRECAUTIONS

Before using, carefully read **CAUTIONS** on label.

Refer to the Safety Data Sheets (SDS) before use.

FOR PROFESSIONAL USE ONLY.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

CLEANUP INFORMATION

Clean spills, spatters, hands and tools immediately after use with soap and warm clean water. After cleaning, flush spray equipment with compliant cleanup solvent to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using solvents.

HOTW 2/05/2026 B66W01310 12 39

HOTW 2/05/2026 B66A01320 13 38

HOTW 2/05/2026 B66N01310 12 39

SP, FRC